

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

SPEC SPRAY ZINC – ALU

PRODUCT DESCRIPTION

High quality zinc repair to rep air minor damage in surface of steel galvanized by immersion. Applications : gutters, drainpipes, tubs, crash barriers, containers, watering cans. Product is characterized by good coverage and excellent adhesion. Is non-fading and UV resistant.



PHYSICAL AND CHEMICAL CHARACTERISTIC

BASIS : acrylic resin
COLOUR : silver
CAPACITY : 500 ml
TEMPERATURE RESISTANCE : to 110°C

Drying time in room temperature:

- **DUST DRY:** after 5-10 min
 - **TACK FREE:** after 10-20 min
 - **HARDENED/RE-SPRAYABLE:** after 2 h

VOC CONTENT

VOC = 670,1 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat.B/5) at the level of 840[g/l] for the ready product.

USAGE

- Best processing temperature is 5 ÷ 30°C.
- Surface should be dry, free from rust and dirt.
- Shake before using for 2 minutes and spray a sample.
- During lacquering hold aerosol in 25÷30 cm distance from the surface.
- Apply zinc repair in several thin layers. Before applying the next layer, again shake the aerosol.
- **Clean the spray nozzle after use!** – Holding the can with the valve pointing downward, press the button emptying the content for about 5 seconds.

Caution: For safety reasons always comply with information provided in the Material Safety Data Sheet.

STORAGE

Store the product components in sealed container, in dry and cool places, away from heat sources, as well as direct sunlight.

EXPIRY DATE

SPEC Spray Zinc-Alu

- 5 years from the production date

PRODUCT

SPEC Spray Zinc-Alu

300006058 (500ml)

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses. Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.
Ząbrowo, Poland