

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

ANTICORROSIVE EPOXY PRIMER



PRODUCT DESCRIPTION

1K primer designed to preparing the surface for the top coating. Product has excellent anticorrosion properties and guarantees very good insulation from moisture. Is perfect to the spot repairs, may be covered by water-based or solvent-based systems*. Can be applied directly on steel, galvanized steel, stainless steel, aluminum and old paint coatings, also can be applied wet-on-wet.

PHYSICAL AND CHEMICAL PROPERTIES

Color: light grey, dark grey
 Capacity: 500 ml
 Base: epoxy resin
 Density: 0,802 g/cm³ (in temp. 20⁰C)
 Curing time: 10 – 15 min / 20⁰C

VOLATILE ORGANIC COMPOUNDS

VOC = 683,4 [g/l]
 The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat. B/5) at the level of 840[g/l] for the ready product.

USAGE

- Surface should be dry sanded, degreased, cleaned and dry.
- Before using shake aerosol can for 2 minutes and try it on cardboard.
- Apply 2-3 layers of the primer for the prepared surface
- **After use clean aerosol's outlets** – hold down aerosol's valve, push the bottom and release contents for 5 seconds.

Caution: For safety reasons always comply with information provided in the Material Safety Data Sheet

STORAGE

Store the product in sealed container, in dry and cool places, away from heat sources, as well as direct sunlight.

WARRANTY PERIOD

SPRAY ANTICORROSIVE EPOXY PRIMER 500 ml - 5 years from production date.

PRODUCT

ART. No.

SPRAY ANTICORROSIVE EPOXY PRIMER 500 ml light grey 300009244 ; dark grey 300009245

LIMITATION OF LIABILITY

The information contained in the TDS is up-to-date and correct on the day the information is released. Because TROTON can not control or predict the conditions under which a product will be used, each user should review information in the specific context of the intended usage. To the maximum extent permitted by applicable law, TROTON shall not be liable for damages of any kind arising from the use or reliance on information contained in this TDS.

Given the variety of factors that can affect the usage and application of the TROTON product, some of which are only within the user's knowledge and control range, it is essential that the user evaluate the TROTON product to determine if the product is fit for a particular purpose and whether the product is suitable for the user's usage.

Under no circumstances shall TROTON be liable to the user or any third party for any indirect, derivative, incidental, special or punitive damages, including loss of profits resulting from the use of products manufactured by TROTON and / or TROTON's services.

All information are based upon the precise laboratory studies and many years of experience. The good market position does not release us from the constant supervision of our products quality. However, we are not responsible for the final effects of the improper storage or application of our products, as well as for work inconsistent with the good craft practice.

TROTON Sp. z o.o.
 Ząbrowo, Poland.

*due to lots of paints and varnishes on the market compatibility test is recommended.