

## TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

### SPRAY UBS ANTI-GRAVEL

WITH STRUCTURE



#### PRODUCT DESCRIPTION

Quick-drying agent based on synthetic resins designed to protect car bodies. Provides long-term protection against the chemical and mechanical factors (including harmful effect of the fuel, oil, water and salt) front and rear of the car bodies, car sills, wheel housings etc. It is characterized by very good adhesion, creates visible structure, doesn't contain asphalts and bitumen. Can be coated with any lacquer systems\*.

#### PHYSICAL AND CHEMICAL PROPERTIES

Colour: black  
 Glass grade: mat  
 Capacity: 500 ml  
 Efficiency: approx 1,75 m<sup>2</sup> dry film 100 µm  
 Density: 0.80 ± 0.02 kg/L (DIN 51757)  
 Drying time in temp. 20°C\*\*: 2 - 3 hours

#### VOLATILE ORGANIC COMPOUNDS

VOC = 578 [g/l]

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat. B/5) at the level of 840[g/l] for the ready product.

#### SUBSTRATE

Product can be applied on :

- Poliester laminate
- Polyester putties
- Epoxy primer
- Two – component acryl filler
- Steel substrate, galvanized steel substrate, stainless steel substrate
- Aluminium substrate
- Wash primer
- Plastic

#### SURFACE PREPARATION

- The polyester laminate should be degreased, dry ground (P80-P120) and degreased again.
- The polyester putties should be dry ground (P120).
- The primer should be degreased, dry ground (P220 – P280) and degreased again.
- The steel substrate should be degreased, dry ground (P80 – P120) and degreased again.
- The stainless steel surface should be degreased.
- The aluminium and galvanized surface should be degreased, dulled with the abrasive cloth and degreased again.
- The old coatings should be degreased, dry ground (P220 – P280) and degreased again.
- On plastic it is recommended to hold it at temperature of 50°C, which is useful to remove silicon from surface.

#### USAGE

- The best results are achieved applying at room temperature. The ambient temperature and the temperature of the product should be the same.
- Shake before using for 2 minutes and try it on cardboard.
- During lacquering hold aerosol in 25±30 cm distance from the surface.
- Apply 2 or 3 single layers interval 5 – 10 minutes. Shake aerosol again before applying each layer.
- **Clean the spray nozzle after use!** – Hold the can with the valve pointing downward, press the button emptying the content for about 5 seconds.

**Caution:** For safety reasons always comply with information provided in the Material Safety Data Sheet.

#### STORAGE

Store the product in sealed container, in dry and cool places, away from heat sources, as well as direct sunlight.

#### WARRANTY PERIOD

SPRAY ANTI-GRAVEL UBS WITH STRUCTURE 500 ml

- 3 years from production date.

#### PRODUCT

SPRAY ANTI-GRAVEL UBS WITH STRUCTURE 500 ml

#### ART. No.

300002290

**LIMITATION OF LIABILITY**

The information contained in the TDS is up-to-date and correct on the day the information is released.

Because TROTON can not control or predict the conditions under which a product will be used, each user should review information in the specific context of the intended usage. To the maximum extent permitted by applicable law, TROTON shall not be liable for damages of any kind arising from the use or reliance on information contained in this TDS.

Given the variety of factors that can affect the usage and application of the TROTON product, some of which are only within the user's knowledge and control range, it is essential that the user evaluate the TROTON product to determine if the product is fit for a particular purpose and whether the product is suitable for the user's usage.

Under no circumstances shall TROTON be liable to the user or any third party for any indirect, derivative, incidental, special or punitive damages, including loss of profits resulting from the use of products manufactured by TROTON and / or TROTON's services.

All information are based upon the precise laboratory studies and many years of experience. The good market position does not release us from the constant supervision of our products quality. However, we are not responsible for the final effects of the improper storage or application of our products, as well as for work inconsistent with the good craft practice.

TROTON Sp. z o.o.  
Ząbrowo, Poland.

\*Due to the large number of paints and varnishes on the market it's recommended to conduct compatibility test.

\*\*Drying time depends on air temperature, humidity and thickness of the layer.