

## TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

### addsTROTON 2 in 1 ANTI GRAVEL / SEAM SEALANT



#### PRODUCT DESCRIPTION

Product is based on rubber and synthetic resin, designed to protect car bodies against mechanical damages, rust and harmful effect of the weather conditions, and also seal joints and welds using the spray gun. Sealant has also soundproofing properties. After drying can be covered with all conventional lacquer systems.

#### PHYSICAL AND CHEMICAL PROPERTIES

- Color: black, grey
- Density\*: 1,21 – 1,25 kg/l
- Capacity: 1 ltr
- Efficiency:  $\pm 0,7 \text{ kg/m}^2$  ( $\pm 600 \mu$  wet layer)
- Temp. resistance (after curing): - 25<sup>0</sup>C do +80<sup>0</sup>C
- Viscosity (Brookfield)\*: 4,250 m.Pa.s

#### Drying time\*:

- Touch dry: approx. 45 min. ( $\pm 700 \mu$ )
- Completely dry: approx. 3,5 h. ( $\pm 700 \mu$ )

\* temp. 20<sup>0</sup>C, RH 65%

#### CONTENT OF VOLATILE COMPONENTS

VOC = 559,4 [g/l]

This product complies with Directive 2004/42/EC that for this category of products (cat.B/5) provides the threshold value of volatile components' share at the level of 840 [g/l] in the ready for use product.

**USAGE**Antigravel coating

- Covered surface should be clean, free of dust, grease and rust.
- Shake well can before use.
- Product can be applied using gun with an air-pressure of 3 -6 bar.
- Recommended spraying distance is about 30 cm.
- If the intention is to obtain a thicker coating it is recommended to dry the layers in between.
- Equipment and contaminated surface can be cleaned in fresh condition with solvents. After curing product can be remove only mechanical.
- Depends of the thickness of the coating, after about 60 - 90 minutes surface can be covered by 2k or basecoat lacquers. Before use of 2k lacquers it is recommended to use a primer according to instruction of paint supplier.

Sealing

- Covered surface should be clean, free of dust, grease and rust.
- Shake well can before use.
- Product can be applied using gun with an air-pressure of 2 - 4 bar.
- Recommended spraying distance is about 1 - 2 cm.
- If the intention is to obtain a thicker coating it is recommended to dry the layers in between.
- Equipment and contaminated surface can be cleaned in fresh condition with solvents. After curing product can be remove only mechanical.
- Depends of the thickness of the coating, after about 3 hours surface can be covered by 2k or basecoat lacquers. Before use of 2k lacquers it is recommended to use a primer according to instruction of paint supplier.

**STORAGE**

Store the product in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight. Storage temperature 10 - 30°C.

**EXPIRY DATE**

2 years from production date.

**Important Information:**

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at [www.troton.com.pl](http://www.troton.com.pl) or will be sent according to your request: [troton@troton.com.pl](mailto:troton@troton.com.pl)

**Technical Information:** The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

**Limitation of Liability:** Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information..

TROTON Sp. z o.o.  
Ząbrowo, Poland