

TECHNICAL INFORMATION

PRODUCT FOR PROFESSIONAL USE ONLY

addsTROTON SPRAY COLOR PAINT acryl



PRODUCT DESCRIPTION

Quick-drying lacquers, with the excellent covering properties and of good adhesion directly to metal (except stainless steel) wood, concrete and brick. Resistant to small mechanical damages and weather conditions, including UV radiation.

PHYSICAL AND CHEMICAL PROPERTIES

Color*: red RAL 3020, intensive red RAL3002, yellow RAL1028,
blue RAL5002, green RAL 6029, gray RAL7001,
dark gray RAL7016, brown RAL8016, white RAL9010

*color approx. 80% similar to the color of the RAL table

Gloss grade: gloss
Capacity: 400 ml
Yield: 1 – 2 m²/ 400 ml
Resin: Pure Acrylic Resin
Solids: 10 – 25 % (m/m)
Density: 0.85 – 0.95 kg./l.
Thinner : acetone

Opacity: 1 to 2 layers (depending on the film thickness)
Film thickness : 50 to 100 µm wet (depending on the wanted structure)

Drying time in 20°C:

- Dust dry: 5 – 8 min. (appr.)
- Tack free: 60 min. (appr.)
- Hard dry: 24 hours (appr.)

*drying time depends on the temperature, humidity and thickness of the coating.

CONTENT OF VOLATILE MATTER

TROTON Sp. z.o.o

Address: Ząbrowo 14A, 78-120 Gościno, Poland, Tel: +48 94 35 123 94

Tel/Fax: +48 94 35 126 22 Website: www.troton.com.pl Email: troton@troton.com.pl

VOC=650 [g/l].

This product satisfies requirements of the European Union Directive (2004/42/WE), which for this product category (B/5) gives the limit value of content of volatile matter at the level of 840 [g/l] of the ready-for-use product.

APPLICATION

- Clear the surface carefully, dry and degrease.
- Cover the parts which should not be painted.
- Shake before using for 2 – 3 minutes and try it on cardboard.
- Spray paint on the surface from a distance of approx. 25 cm.
- Spray one or two thin layers (as needed).
- After use clean aerosol's outlets – hold down aerosol's valve, push the bottom and release contents for 5 seconds.

Caution: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.

STORAGE

Store the product components in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight.

WARRANTY PERIOD

5 years from the production date.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values.

Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.
Ząbrowo, Poland