

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

*adds***TROTON** **SPRAY** **ANTIGRAVEL - UBS**



PRODUCT DESCRIPTION

Product based on synthetic resins designed to protect car bodies against the harmful effect of the weather conditions, fuel, oil, water and salt. Product creates a strong, flexible anti-gravel layer with soundproofing and anticorrosive properties. Can be coated with any lacquer systems. Doesn't contain bitumen.

PHYSICAL AND CHEMICAL PROPERTIES

Color:	black, white, grey
Capacity:	500 ml.
Glass grade:	matt
Drying time in 20 ⁰ C*:	
• dust dry	after approx. 30 min.
• tack free	after approx. 60 min.
• re-sprayable	after approx. 2 hours
Temperature resistance :	between -20 ⁰ C and 80 ⁰ C when applied and full dry

VOLATILE COMPONENTS CONTENT

VOC = 579 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat. B/5) at the level of 840[g/l] for the ready product.

*drying time depends on the temperature, humidity and thickness of the coating.

SUBSTRATE AND SURFACE PREPARATION

The product shows very good adhesion to the following substrates:

- polyester laminates
- polyester putties
- epoxy primers
- two-component acryl fillers
- steel substrates,
- steel rustless surfaces
- aluminium substrate,
- plastic materials
- wash primer

Polyester laminates should be degreased, dry ground (P80-P120) and degreased again.

Polyester putty should be degreased, dry ground (P120).

Stainless material should be degreased.

Steel surface should be degreased, dry ground (P80 – P120) and degreased again.

Aluminium and galvanized surface should be degreased, dulled with the abrasive cloth and degreased again.

Old coatings should be degreased, dry ground (P220 – P280) and degreased again.

Plastic surface should be clean by water and detergent, dulled with the abrasive cloth and degreased again. We recommended warming the plastic element to a temperature of 200C, with facilitates the removal of any silicone from the surface.

USAGE

- Best temperature for application 15-25 °C.
- Shake the bottle before use for about 2 min and try spray on cardboard first.
- Spray the surface from a distance of about 25-30 cm. Apply 2-3 individual layers of the agent within a time interval 2-5 minutes. Shake the bottle in between the application of each following layer.
- **Clean the spray nozzle after use!** – Holding the can with the valve pointing downward, press the button emptying the content for about 5 seconds.

In case of direct application on steel surface we recommended imposition of the top layer of lacquer or enamel.

Caution: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.

STORAGE

Store the product components in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight.

EXPIRY DATE

5 years from the production date.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.

TROTON Sp. z.o.o

Address: Ząbrowo 14A, 78-120 Gościno, Poland, Tel: +48 94 35 123 94

Tel/Fax: +48 94 35 126 22 Website: www.troton.com.pl Email: troton@troton.com.pl

Ząbrowo, Poland